



AQUACIM

HYDRAULIC CEMENT WITH CATALYST



7 good reasons for using AQUACIM

1. Very **fast-setting**: around 15 min. **Traffic after 1 hour**.
2. **Easy** to use repairs.
3. Produces an **exothermic** reaction of approximately 22 °C.
4. **Hardens** evenly.
5. **Grips** the edges of the repair so does **not retract** on drying.
6. Can be used with temperatures up to - 20 °C.
7. **Paintable** after 1 week of drying.

Particularly suitable for use in



Supermarkets



Industry



Public buildings



Construction

To repair crumbling, steps edges, cracks, flaws in cement, concrete or by-products.
 On horizontal surfaces, to fix studs, legs and metallic supports.
 On vertical surfaces, to repair, to fill cracks and to fix small hooks.
 To repair stone floors jointing, smooth easily.

Characteristics	Instructions for use
Compression resistance: After 1 hour 302 kg per cm ² After 7 days 550 kg per cm ² Appearance grey powder. Density: 2.7. Can be applied in all weathers, the characteristics of drying and resistance not being affected by the heat, the cold or by humidity. For more information: see MSDS.	Always mix with 1 litre of water for 3 kg of AQUACIM. As the product is fast-setting, prepare only small quantities to use in 10 minutes. Add the water very slowly, while mixing to obtain a thick dough consistency. Wait for one minute. Then add water to obtain the consistency required. Moisten the surface to be treated, pour AQUACIM carefully without creating air bubbles. For deep repairs, eliminate air bubbles by pushing a metallic stalk in and out of the repair. In the case of use in temperatures below 0 °C, moisten the hole and prepare the mixture with some hot, even boiling water. Clean the equipment with water, immediately after use.

GB10092019/2

7+

POLYCIM : Mortar with resins, rapid setting.

This datasheet supersedes previous documents. The information contained in these data sheets is based on our present knowledge and experience and is given as indication only. Under no circumstances does it engage our responsibility in the event of misuse of our products. Non-contractual photos and images.



Tél 02 97 54 50 00
www.7darmor.fr

