

CONVEROX

RUST CONVERTER



7 good reasons for using CONVEROX A

1. Brown in colour, during application becomes lightly bluish and turns **blue-black** after 10 minutes.
2. **Glossy**.
3. **No break** in the film if folded and **resists impacts** until metal is broken.
4. **Resistant** to water, acids and diluted bases, as well as to temperatures up to 80°C.
5. **Adhesion**: 100% of adhesion result in squaring test. Forms an excellent base for finishing paints.
6. Reacts with rust and forms an **organic-metallic barrier** within 10 minutes after application. Corrosion is disactivated permanently.
7. **Protects** the metal: penetrates the oxidised layer and combines and fixes on the undamaged metal beneath.

Particularly suitable for use in



Public buildings



Construction

Restores and protects all metallic materials subject to tough conditions (building yard equipment, public works, quarries, iron works, chassis and bodies of cars, agricultural machinery, ship-yards, etc...).

Characteristics	Instructions for use
<p>Composition: brown synthetic resin Density: 1.06 Dry extract: higher than 50% Covering capacity: approx. 20m² per litre</p> <p><u>Drying</u> Dust protection 30 minutes, Dry and hard 24 hours.</p> <p>For more information, see MSDS.</p>	<p>Use neat or diluted up to 30% with water. Apply with brush, roller, spray gun or by dipping. By dipping, just several seconds are sufficient. For heavily rusted surfaces, it is recommended to lightly brush off all unfixed rust and to apply 2 coats to neutralize the complete rust layer. Degrease surfaces to be treated, if necessary. For optimal protection, we advise to paint on the CONVEROX coat approximately 24 hours after drying. It is not recommended to leave parts immersed in CONVEROX. Do not use CONVEROX under 10°C.</p>

GB08022016/4

7 +

SOLVCLEAN : Degreaser for surface preparations.

This datasheet supersedes previous documents. The information contained in these data sheets is based on our present knowledge and experience and is given as indication only. Under no circumstances does it engage our responsibility in the event of misuse of our products. Non-contractual photos and images.



Tél 02 97 54 50 00
Www.7darmor.fr

7d'Armor