

TRAFFIC 200H

REGISTERED ROAD PAINTS FOR STREET MARKING





7 good reasons for using TRAFFIC 200H

- 1. Based on acrylic resins in solvent phase.
- 2. Covers well. Very good adhesion on road surfaces.
- 3. Dries very quickly.
- 4. Moves with the asphalt.
- 5. Good resistance to traffic.
- 6. **Temperature** resistant.
- 7. After drying, matt finish.

Particularly suitable for use in



Public building:



Food trade

For road markings such as markings for centre lines, pedestrian crossings, fog lines, directional arrows, car park marking, traffic separation lines, pavement edging.... Applies to bitumen, cement, concrete.

Characteristics

Composition: acrylic solvent resins.

Density: 1.58

Dry matter weight: 76 %

Drying time:

- clean condition: 5 mn

- touch dry: 17 mn

Yield: 1.3 m² / kg for 12 to 14 meters linear with a 10 cm wide

Lifespan: 1,000,000 wheel paths. Registered NF norm: 1RH958S3.

For more information, see MSDS.

Instructions for use

Apply to temperatures superior to 10°C.

Do not apply to wet surfaces.

Shake before using.

Clean, dust the surface before application.

Use neat or diluted with 3 % of D410, depending on the mode of

application and the support.

Applied with a brush, a paint gun or marking machine.

Clean the application equipment before drying with D410.

GB28082018

7 en +

D410: Thinner for polyurethane and epoxy coat.

This datasheet supersedes previous documents. The information contained in these data sheets is based on our present knowledge and experience and is given as indication only. Under no circumstances does it engage our responsibility in the event of misuse of our products. Non-contractual photos and images



